ILVA TECHNICAL DATA SHEET

PRODUCT CODE: PI 29

DESCRIPTION:	Unsaturated Polyester Black Undercoat		
USES:	Sanding sealer for MDF flat and shaped panels, doors etc. Can be topcoated with matte and gloss polyurethane finshes.		
PRODUCT PREPARATION:	PI29 Black polyester undercoa TVS5AA1 Accelerator* TV84 Long pot life catalyst TZ03 Thinner *use 1 part TVS5AA1 in hot we	2 2 5 - 15	128 2 2 20
APPLICATION SYSTEM:	Double component spray equipment is recommended.		
QUANTITY(grsq mt):	150 - 200 per coat (6-8 wet mils)		
COATS:	2 to 3		
GENERAL PROPERTIES:	Specific Gravity, gr/cc Viscosity* Application Viscosity** Solids by Weight, % Pot Life, minutes at 20°C/68°F *DIN 53211 Nr.4 at 20°C/68°F **DIN 53211 Nr. 4 at 20°C/68°F		
DRYING TIME: (at 20*C/68*F)	Gel time, between coats, minutes For sanding and topcoating, hours		20-30 minimum 24 minimum
TYPICAL SYSTEMS:	Substrate		MDF
	PI29/TVS5AA1/TV84 PM19/TX276 <u>Matte Finish</u> TF25/TV19 PI29/TVS5AA1/TV84	1 coat 2 - 3 coats 2 coats 1 coat 2 - 3 coats 1 coat	40 gr/sq.mt. (1.6 wet mils) 150/200 gr/sq.mt. per coat (6-8 wet mils) 150 gr/sq.mt. (6 wet mils) 40 gr/sq.mt. (1.6 wet mils) 150/200 gr/sq.mt. per coat (6-8 wet mils) 150 gr/sq.mt. (6 wet mils)
SHELF LIFE:	12 Months		
STORAGE:	Store in a tightly closed container at room temperatures (18-25°C/64-75°F) and protect from moisture and f foreign material.		
DATE OF ISSUANCE:	06-10, Revised 12-13, 5-16, 7-20, 12-20, 5-22, 5-23		
IC & S, P.O. BOX 10845, LANCASTER, PA 17605			

(800) 220-4035

EVERY REASONABLE PRECAUTION IS TAKEN IN THE MANUFACTURE OF OUR PRODUCTS TO INSURE THAT THEY COMPLY WITH OUR STANDARDS. INFORMATION GIVEN IS CORRECT TO THE BEST OF OUR KNOWLEDGE. ANY SUGGESTIONS MADE BY US COVERING THE USE OF OUR PRODUCTS ARE BASED ON EXPERIENCE AND/OR TESTS BELIEVED TO BE RELIABLE. HOWEVER, BECAUSE THE USE OF ANY PRODUCT OF OUR MANUFACTURE IS COMPLETELY BEYOND OUR CONTROL. INCLUDING FOR EXAMPLE, THE METHOD AND CONDITIONS OF APPLICATION, NO GUARANTEE OR WARANTY, EX-PRESSED OR IMPLIED, IS MADE. MANUFACTURER'S MAXIMUM LIABILITY SHALL BE TO REPLACE SUCH QUANTITY OF PRODUCT DETERMINED BY OUR LABORATORY TO BE DEFECTIVE. USER SHALL DETERMINE THE SUITABILITY OF THE PRODUCT FOR HIS INTENDED USE AND ASSUME ALL RISK AND LIABILITY IN CONNECTION THEREWITH.