## ILVA TECHNICAL DATA SHEET

PRODUCT SERIES: KLIMA SERIES

PRODUCT CODE: HTM5077

DESCRIPTION: KLIMA WB Clear 5 Sheen Topcoat

Thixotropic topcoat based on acrylic based resins in water dispersion for wood protection. Recommended to add PZ4xx colorants at 0.1-0.5% to enhance performance, or add up to 10% PZ5xx colorants to make deep tone colors. Not intended to be used as a clear finish as it will amber, and without

pigment, performance will suffer.

**USES:** For outdoor use, pre-coated with Klima Aquatech series impregnating stains and sealers.

May be used over TN40 Sealer of as a self-sealer.

**PRODUCT** 

PREPARATION: HTM5077 WB Clear Topcoat 100 parts by weight or volume

Water Thinner 5 parts by weight or volume

APPLICATION SYSTEM: For best results use Kremlin 30:1 pump with Airmix 600 fluid lbs, 35-40 static atomizing air

06134/06154 tips or use conventional, pressure pot, cup gun or apply by roller or brush. To

brush use PX0/03 at 2-3%.

**FILM THICKNESS:** 7 mils wet per coat, for a total of 14 mils wet.

COATS: 2 coats to achieve minimum wet film thickness of 14 mils

**GENERAL PROPERTIES**: Specific Gravity, gr/cc 1.029+/-.02

Viscosity as supplied (Ford 6 Cup) 58 +/-5 secs Solids, % by weight: 40 +/-2

Thinner: Water or PX0/03

% of dilution: Water at 5-20% depending upon

equipment PX0/03 at 2-3%

**DRYING TIME:** Air Dry with ventilation, dry to handle:

(at 20°C/68°F) Dust Free: 20 minutes

Dry to touch: 1 hour
Full dried: 2-4 hours
Sanding: 2-4 hours

(Drying times can vary according to temperature, ventialtion and relative humidity)

COATING CYCLES: Cycle 1 - High Quality with Thixotropic Topcoat

Substrate Pine or soft woods

Impregnating: PN 3/color - 1 coat - 1-2 hours drying
Sealer: TN40 - 1 coat - 2-4 hours before sanding

Topcoat: HTM5077 - 1 coat

Before using coated items, it is advisable to wait 3 days. Minimum room temperature during

application and drying should be 60°F

CONTINUED ON NEXT PAGE...

IC & S, P.O. BOX 10845, LANCASTER, PA 17605 (800) 220-4035

EVERY REASONABLE PRECAUTION IS TAKEN IN THE MANUFACTURE OF OUR PRODUCTS TO INSURE THAT THEY COMPLY WITH OUR STANDARDS. INFORMATION GIVEN IS CORRECT TO THE BEST OF OUR KNOWLEDGE. ANY SUGGESTIONS MADE BY US COVERING THE USE OF OUR PRODUCTS ARE BASED ON EXPERIENCE AND/OR TESTS BELIEVED TO BE RELIABLE. HOWEVER, BECAUSE THE USE OF ANY PRODUCT OF OUR MANUFACTURE IS COMPLETELY BEYOND OUR CONTROL, INCLUDING FOR EXAMPLE, THE METHOD AND CONDITIONS OF APPLICATION, NO GUARANTE OR WARANTY, EXPRESSED OR IMPLIED, IS MADE. MANUFACTURER'S MAXIMUM LIABILITY SHALL BE TO REPLACE SUCH QUANTITY OF PRODUCT DETERMINED BY OUR LABORATORY TO BE DEFECTIVE. USER SHALL DETERMINE THE SUITABILITY OF THE PRODUCT FOR HIS INTENDED USE AND ASSUME ALL RISK AND LIABILITY IN CONNECTION THEREWITH.

## **ILVA TECHNICAL DATA SHEET**

PRODUCT SERIES: KLIMA SERIES

PRODUCT CODE: HTM5077

COATING CYCLES: Cycle 2 - General use as self-sealer

Substrate Pine or soft woods

Impregnating: PN 3/color - 1 coat - 1-2 hours drying

Light Sanding with scotchbrite

Topcoat: HTM5077 - 1 coat - dry 2-4 hours - sand with 280 grit

Topcoat: HTM5077 - 1 coat

**PRODUCT** 

**PROPERTIES:** This product improves the protective action of the impregnating products and protects the

substrate from photochemical degradation thanks to the presence of special UV absorbers. Soft to the touch and highly flexible, no sanding when applying coat for maintenance so as to

allow easy maintenance.

MAINTENANCE: Items already coated with HTM5077 topcoat should have dirt and other residuals removed

and be topcoated with the Klima TN030 products.

WARNINGS: Keep from Freezing!

SHELF LIFE: 12 Months

STORAGE: Store in a tightly closed container at room temperatures (18-25 °C/64-75 °F) and protect

from moisture and foreign material. Do not store at temperatures below 7°C (45°F).

**DATE OF ISSUANCE:** 03-18, 4-19