ILVA TECHNICAL DATA SHEET

PRODUCT CODE:	PL 50					
DESCRIPTION:	Polyurethane White Satin Finish					
USES:	Polyurethane white matte topcoats, suitable for open and closed grain systems, for flat panels and assembled furniture.					
PRODUCT PREPARATION:	PL50 Polyurethane White Ma TX75 Hardener (non-yellowir TZ13 Thinner		<u>Parts by</u> 100 40 15-30	<u>weight</u>	<u>Parts by volume (ounces)</u> 128 64 30	
APPLICATION SYSTEMS:	Airless, air-assisted, conventional spray.					
QUANTITY:	120 140 per coat(gr sq mt) (4.8-5.6 wet mils)					
COATS:	One					
GENERAL PROPERTIES:	Specific Gravity, gr/cc Viscosity* Application Viscosity*spray Solids by Weight, %, as supplied Solids by Weight, %, ready to use Pot Life, hours at 20°C/68°F		1.28 +/- 0.05 85 +/- 2 sec 10 +/- 2 sec 62 +/- 2 40-45 3			
	* ASTM D1200 (Ford) #4 at 20°C/68°F					
DRYING TIME: (at 20*C/68*F)	To handle: To stack:			1 hour Over night		
AVAILABLE SHEENS:	PL50 25-30 Sheen					
TYPICAL SYSTEMS:	Substrate:			MDF (closed grain), Ash (open grain)		
	Open Grain Finish					
	PA20/TX50 PL50/TX75	1 coat 1 coat			q mt. (4.8 wet mils) q mt. (4.8 wet mils)	
	Closed Grain Finish					
	TF25/TV19 PI40/TVS5AA1/TV84 PL50/TX75	1 coat 2-3 coat 1 coat	S	150/200	mt (1.6 wet mils) gr/sq mt (6-8 wet mils) q mt. (4.8 wet mils)	
SHELF LIFE:	18 Months					
STORAGE:	Store in a tightly closed container at room temperatures (18 -25 °C/64 -75 °F) and protect from moisture and foreign material.					
DATE OF ISSUANCE:	03 - 97 Revised 12-13, 5-14, 5-16, 9-16, 10-17, 4-18, 9-18, 7-20, 12-20, 5-23					

IC & S, P.O. BOX 10845, LANCASTER, PA 17605 (800) 220-4035

EVERY REASONABLE PRECAUTION IS TAKEN IN THE MANUFACTURE OF OUR PRODUCTS TO INSURE THAT THEY COMPLY WITH OUR STANDARDS. INFORMATION GIVEN IS CORRECT TO THE BEST OF OUR KNOWLEDGE. ANY SUGGESTIONS MADE BY US COVERING THE USE OF OUR PRODUCTS ARE BASED ON EXPERIENCE AND/OR TESTS BELIEVED TO BE RELIABLE. HOWEVER, BECAUSE THE USE OF ANY PRODUCT OF OUR MANUFACTURE IS COMPLETELY BEYOND OUR CONTROL. INCLUDING FOR EXAMPLE. THE METHOD AND CONDITIONS OF APPLICATION, NO GUARANTEE OR WARANTY, EX-PRESSED OR IMPLIED, IS MADE. MANUFACTURER'S MAXIMUM LIABILITY SHALL BE TO REPLACE SUCH QUANTITY OF PRODUCT DETERMINED BY OUR LABORATORY TO BE DEFECTIVE. USER SHALL DETERMINE THE SUITABILITY OF THE PRODUCT FOR HIS INTENDED USE AND ASSUME ALL RISK AND LIABILITY IN CONNECTION THEREWITH.