ILVA TECHNICAL DATA SHEET

PRODUCT CODE: TA 03

DESCRIPTION: Polyurethane Clear Sealer

USES: Sealer for polyurethane clear systems, suitable for skirting boards, panels, frames, doors and assembled

furniture.

PRODUCT PREPARATION: Parts by weight Parts by volume (ounces)

 TA03
 Polyurethane Clear Sealer
 100
 128

 TX50*
 Hardener
 50
 64

 TZ33
 Thinner
 0 - 10
 0-20

* TX75 for non-yellowing 40 50

APPLICATION SYSTEM: Airless, Air-assisted, or Conventional Spray

QUANTITY: 120 - 140 per coat (gr. sq. mt.) (4.8-5.6 wet mils)

COATS: One - for open grained systems

GENERAL PROPERTIES: Specific Gravity, gr/cc 0.97 +/- 0.05

* ASTM D1200 (Ford) #4 at 20°C/68°F

DRYING TIME: Handling: 30 - 40 minutes

(at 20*C/68*F) Sanding and topcoating: 8 hours minimum

TYPICAL SYSTEMS: Substrate: Various woods

Open Grain Finish

TA03/TX50* 1 coat 120 gr/sq. mt. (4.8 wet mils) TO9 Series/TX24 1 coat 120 gr/sq. mt. (4.8 wet mils)

* TX75 for non-yellowing

SHELF LIFE: 18 Months

STORAGE: Store in a tightly closed container at room temperatures (18 -25 °C/64 -75 °F) and protect from moisture

and foreign material.

DATE OF ISSUANCE: 03 - 97 Revised 12-13, 5-16, 10-17, 10-20, 12-20

IC & S, P.O. BOX 10845, LANCASTER, PA 17605 (800) 220-4035

EVERY REASONABLE PRECAUTION IS TAKEN IN THE MANUFACTURE OF OUR PRODUCTS TO INSURE THAT THEY COMPLY WITH OUR STANDARDS. INFORMATION GIVEN IS CORRECT TO THE BEST OF OUR KNOWLEDGE. ANY SUGGESTIONS MADE BY US COVERING THE USE OF OUR PRODUCTS ARE BASED ON EXPERIENCE AND/OR TESTS BELIEVED TO BE RELIABLE. HOWEVER, BECAUSE THE USE OF ANY PRODUCT OF OUR MANUFACTURE IS COMPLETELY BEYOND OUR CONTROL, INCLUDING FOR EXAMPLE, THE METHOD AND CONDITIONS OF APPLICATION, NO GUARANTEE OR WARANTY, EXPRESSED OR IMPLIED, IS MADE. MANUFACTURER'S MAXIMUM LIABILITY SHALL BE TO REPLACE SUCH QUANTITY OF PRODUCT TETERMINED BY OUR LABORATORY TO BE DEFECTIVE. USER SHALL DETERMINE THE SUITABILITY OF THE PRODUCT FOR HIS INTENDED USE AND ASSUME ALL RISK AND LIABILITY IN CONNECTION THEREWITH.