ILVA TECHNICAL DATA SHEET

PRODUCT SERIES: KLIMA SERIES

PRODUCT CODE: TN931

DESCRIPTION: KLIMA WB Wood Tone Satin Topcoat

Thixotropic topcoat based on acrylic based resins in water dispersion for

wood protection. Suitable for hardwoods and softwoods.

USES: For outdoor use, pre-coated with KLIMA series Aquatech impregnating stains and sealers.

May be used over TN40 Sealer or as a self-sealer.

PRODUCT

PREPARATION: TN931 WB Wood Tone Self-Sealer 100 parts by weight or volume

Water Thinner 5 parts by weight or volume

APPLICATION SYSTEM: For best results use Kremlin 30:1 pump with Airmix 600 fluid lbs, 35-40 static atomizing air

06134/06154 tips or use conventional, pressure pot, cup gun or apply by roller or brush. To

brush use TZ08 at 5%.

FILM THICKNESS: 7 mils wet per coat, for a total of 14 mils wet.

COATS: 2 coats to achieve minimum wet film thickness of 14 mils.

GENERAL PROPERTIES: Specific Gravity, gr/cc 1.050+/-.02

Viscosity as supplied* 38,000-41,000 cps

Solids, % by weight: 40 +/-2

Thinner: Water - TZ07 or TZ08

% of dilution: 5-20% depending upon equipment

* (Brookfield Aspo n°4 vel 2.5)

DRYING TIME: Air Dry with ventilation, dry to handle:

(at 20°C/68°F) Dust Free: 20 minutes

Dry to touch: 1 hour
Full dried: 2-4 hours
Sanding: 2-4 hours

(Drying times can vary according to temperature, ventialtion and relative humidity)

COATING CYCLES: Cycle 1 - High Quality with Thixotropic Topcoat

Substrate Pine or soft woods

Impregnating: PN 3/color - 1 coat - 1-2 hours drying
Sealer: TN40 - 1 coat - 2-4 hours before sanding

Topcoat: TN931 - 1 coat

Before using coated items, it is advisable to wait 3 days. Minimum room temperature during

application and drying should be 60°F

CONTINUED ON NEXT PAGE...

IC & S, P.O. BOX 10845, LANCASTER, PA 17605 (800) 220-4035

ILVA TECHNICAL DATA SHEET

PRODUCT SERIES: KLIMA SERIES

PRODUCT CODE: TN931, page 2

COATING CYCLES: Cycle 2 - General use as self-sealer

Substrate Pine or soft woods

Impregnating: PN 3/color - 1 coat - 1-2 hours drying

Light Sanding with scotchbrite

Topcoat: TN931 - 1 coat - dry 2-4 hours - sand with 280 grit

Topcoat: TN931 - 1 coat

PRODUCTThis product improves the protective action of the impregnating products and protects the substrate from photochemical degradation thanks to the presence of special UV absorbers.

Soft to the touch and highly flexible, no sanding when applying coat for maintenance so as to

allow easy maintenance.

MAINTENANCE: Items already coated with TN931 topcoat should have dirt and other residuals removed and

be topcoated with the Klima TN030 products.

WARNINGS: Keep from Freezing!

SHELF LIFE: 12 Months

STORAGE: Store in a tightly closed container at room temperatures (18 -25 °C/64 -75 °F) and protect

from moisture and foreign material. Do not store at temperatures below 7°C (45°F).

DATE OF ISSUANCE: 03-13, Revised 6-15, 2-18, 4-19