

## ILVA TECHNICAL DATA SHEET

**PRODUCT CODE:** PZ3.../COLOR SERIES

**DESCRIPTION:** POLYURETHANE PIGMENTED TINT PASTE

**USES:** Tinting colors for Polyurethane Products. In general they may be used in all polyurethane systems at a level of 20-30% maximum combined color level with no effect on film properties, only gloss levels at the maximum level of tint paste. If used in Acrylic Urethane maximum level is 10%

<b>AVAILABLE COLORS:</b>	<b>PZ330</b> White <b>PZ331</b> Vivid Yellow <b>PZ332</b> Gold Yellow <b>PZ333</b> Yellow Oxide <b>PZ335</b> Wisteria Red <b>PZ336</b> Red Oxide <b>PZ337</b> Bordeaux <b>PZ338</b> Blue <b>PZ339</b> Black <b>PZ340</b> Green <b>PZ341</b> Lemon Yellow <b>PZ344</b> Vivid Red <b>PZ347</b> Violet <b>PZ355</b> Red Concentrate <b>PZ361</b> Yellow <b>PZ364</b> Orange
--------------------------	---

CHEMICAL/PHYSICAL PROPERTIES	CODE	Density (Kg/l)	Density (lb/US gal)	Solid content %
	PZ330	1.877 +/- 0.030	15.7 +/- 0.3	74.0 +/- 2
	PZ331	0.987 +/- 0.030	8.2 +/- 0.3	48.0 +/- 2
	PZ332	1.081 +/- 0.030	9.0 +/- 0.3	49.0 +/- 2
	PZ333	1.550 +/- 0.030	12.9 +/- 0.3	54.0 +/- 2
	PZ335	0.995 +/- 0.030	8.3 +/- 0.3	35.0 +/- 2
	PZ336	1.608 +/- 0.030	13.4 +/- 0.3	39.0 +/- 2
	PZ337	1.056 +/- 0.030	8.8 +/- 0.3	54.0 +/- 2
	PZ338	1.071 +/- 0.030	8.9 +/- 0.3	32.0 +/- 2
	PZ339	1.040 +/- 0.030	8.7 +/- 0.3	44.0 +/- 2
	PZ340	1.074 +/- 0.030	9.0 +/- 0.3	46.0 +/- 2
	PZ341	1.590 +/- 0.030	13.3 +/- 0.3	68.0 +/- 2
	PZ344	1.028 +/- 0.030	8.6 +/- 0.3	39.0 +/- 2
	PZ347	1.038 +/- 0.030	8.7 +/- 0.3	38.0 +/- 2
	PZ355	1.081 +/- 0.030	9.0 +/- 0.3	56.0 +/- 2
	PZ361	1.091 +/- 0.030	9.1 +/- 0.3	48.0 +/- 2
	PZ364	1.102 +/- 0.030	9.2 +/- 0.3	43.0 +/- 2

**USAGE INDICATIONS:** Must thoroughly mix paste before use. It is advisable to add pastes under mechanical mixing. Quantities must be weighed with high precision balances.

**SHELF LIFE:** One Year

**STORAGE:** Store in a tightly closed container at room temperature 18-25°C, 64-75°F and protect from moisture and foreign material.

**DATE OF ISSUANCE:** 12-16

**IC & S, P.O. BOX 10845, LANCASTER, PA 17605  
(800) 220-4035**

EVERY REASONABLE PRECAUTION IS TAKEN IN THE MANUFACTURE OF OUR PRODUCTS TO INSURE THAT THEY COMPLY WITH OUR STANDARDS. INFORMATION GIVEN IS CORRECT TO THE BEST OF OUR KNOWLEDGE. ANY SUGGESTIONS MADE BY US COVERING THE USE OF OUR PRODUCTS ARE BASED ON EXPERIENCE AND/OR TESTS BELIEVED TO BE RELIABLE. HOWEVER, BECAUSE THE USE OF ANY PRODUCT OF OUR MANUFACTURE IS COMPLETELY BEYOND OUR CONTROL, INCLUDING FOR EXAMPLE, THE METHOD AND CONDITIONS OF APPLICATION, NO GUARANTEE OR WARRANTY, EXPRESSED OR IMPLIED, IS MADE. MANUFACTURER'S MAXIMUM LIABILITY SHALL BE TO REPLACE SUCH QUANTITY OF PRODUCT DETERMINED BY OUR LABORATORY TO BE DEFECTIVE. USER SHALL DETERMINE THE SUITABILITY OF THE PRODUCT FOR HIS INTENDED USE AND ASSUME ALL RISK AND LIABILITY IN CONNECTION THEREWITH.